



# AQUATUF® HM-337 (Comp)

Ravago Manufacturing Americas - High Density Polyethylene

Wednesday, January 8, 2025

## General Information

### Product Description

HM-337 is a high-density polyethylene compound designed for applications like kayaks or boats that require a balance very high stiffness and extreme toughness.

#### Key Features:

- Good moldability
- Excellent long term outdoor weatherability (UV15)
- Superior balance of toughness and rigidity
- Very High Stiffness
- Excellent low temperature impact
- Compounded for uniform additive dispersion
- Natural as well as standard, custom or special effect colors available
- Stock colors may be available. See Stock color bulletin
- Also available in powder form as HMP-337

### General

Material Status	• Commercial: Active		
Availability	• North America		
Features	• Good Moldability • Good Toughness	• Good Weather Resistance • High Rigidity	• High Stiffness • Low Temperature Impact Resistance
Appearance	• Colors Available	• Natural Color	
Forms	• Pellets		
Processing Method	• Compression Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.951		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Compression Molded)	3200	psi	ASTM D638
Tensile Elongation (Break, Compression Molded)	350	%	ASTM D638
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in		HB	
0.12 in		HB	

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

**Bamberger Amco Polymers' Disclaimer Statement:** Bamberger Amco Polymers ("BAP") is not the manufacturer of this Product, and BAP has not tested, designed, altered, or modified the Product in any way. BAP does not independently test the Product or verify the information provided in this document. The information provided in this document was provided by the manufacturer, and BAP disclaims any responsibility for a User's reliance on, and the results of use of, this information. The information included herein is not a BAP warranty of any kind, nor is it intended to be. Users must make their own representative tests to determine the safety and suitability of the Product for its intended use, and Users assume all risks of Product use, whether the Product is used alone or in combination with other materials or as a component part of another product. BAP assumes no obligation or liability for any advice furnished or results obtained with respect to the Product, nor for use of the Product in infringement of any patent. **AS SUCH, BAP DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY, AND FITNESS FOR ANY PARTICULAR PURPOSE OR USE.** The foregoing limitation of remedy and exclusion of liability is reflected in, and is part of, the consideration for the price charged for the Product.